TECHNICAL DATA SHEET



Name Code

LOLA S1 31179 S1 FO SR

Product Range Standard EN ISO Weight Size range Mondopoint Packaging

S1 FO SR 20345:2022 390 grams 35 <> 48 11 10 pairs/carton



TECHNICAL SPECIFICATIONS









(1 shoe in size 42)







(same size)



SOLE

SOLE FEATURES

MICROLIGHT









FOOTBED

The MICROLIGHT® soles, which combine cuttingedge compounds for both the PU foam midsole and the compact PU outsole, excel in lightness, flexibility, and elasticity, while offering exceptional stability and wear resistance.

PROTECTIVE ELEMENTS



Heat-treated and epoxy-coated safety toe cap withstands impacts up to 200 Joules and compressions up to 15 kN. Stainless steel fibers increase durability and beveled edges enhance comfort.

WATERPROOF MICROFIBRE

UPPER

Hypoallergenic microfiber with high breathability, tear, rip, scratch, and friction resistance, plus water-repellent and stain-resistant



LINING

Made from durable multi-layer fabric, this lining offers excellent breathability and moisture wicking. It features SANITIZED* treatment to suppress microorganism growth and prevent odours.



SANITIZED®

Antistatic and anti-odour removable insole with SANITIZED® technology ensuring hygiene and a fresh feeling all day.

EXTRA

Requirement













Test Result

SAFETY TECHNICAL SPECIFICATIONS

Description

Description	weasurement out	riequirement	rest riesuit
TOE CAP: Impact resistance	mm	≥ 14	18
TOE CAP: Compression resistance	mm	≥ 14	17
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	-
FOOTWEAR: Antistatic properties (in wet condition)	МΩ	≥ 0,1	71
FOOTWEAR: Antistatic properties (in dry condition)	МΩ	≤ 1.000	122
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	1,8
UPPER: Water vapour coefficient	mg/cm2	≥ 15	17
UPPER: Water penetration after 60 min	g	≤ 0,2	•
UPPER: Water absorption after 60 min	%	≤ 30	-
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	85,5
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	725,9
OUTSOLE: Abrasion resistance	mm3	≤ 150	62
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	32
OUTSOLE: Flexural resistance	mm	≤ 4	0
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	6,9
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	1,7

Measurement Unit

ADDITIONAL FEATURES

Measurement Unit	Requirement	Results
mΔ		
IIIA	≤ 1,00	-
-	autsoles shall not melt and develop any cracks when bent	-
°C	≤ 10	-
°C	≤ 22	-
cm2	after 80 min.	-
ΜΩ	≤ 100	-
	°C cm2	- develop any cracks when bent °C ≤ 10 °C ≤ 22 cm2 after 80 min.

SOLE DESIGN AND PERFORMANCE



TRACTION STABILITY GRIP BRAKING SELF-CLEANING LADDER GRIP

ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

0 MINIMUM VALUE 20 TEST RESULT 29

INDUSTRIES





STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat.
 Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

