TECHNICAL DATA SHEET



Name Code

61111N O1 FO SR YPSILON NEOS O1 FO

EN ISO Standard Weight **Product Range** Size range Mondopoint **Packaging** 01 F0 SR 10 pairs/carton 20347:2022 390 grams 35 <> 50 10,5 (1 shoe in size 42) (same size)



TECHNICAL SPECIFICATIONS



















SOLE

SOLE FEATURES











DUBLE

FORMULA

PROTECTIVE ELEMENTS

UPPER LINING **FOOTBED**



and treated for a velvety touch,

for daily work.

mbines softness with resilience



featuring a microchannel network for unparalleled breathability and antimicrobial properties to prevent



odors and microorganism growth.

removable insole with SANITIZED® technology ensuring hygiene and a fresh feeling all day.



Requirement



Test Result











Description

Description	weasurement out	riequirement	Test Hesuit
TOE CAP: Impact resistance	mm	≥ 14	-
TOE CAP: Compression resistance	mm	≥ 14	-
ANTI-PUNCTURE PLATE: Penetration resistance	N	≥ 1.100	-
FOOTWEAR: Antistatic properties (in wet condition)	МΩ	≥ 0,1	4,7
FOOTWEAR: Antistatic properties (in dry condition)	МΩ	≤ 1.000	111
UPPER: Water vapour permeability	mg/cm2*h	≥ 0,8	9,6
UPPER: Water vapour coefficient	mg/cm2	≥ 15	84,9
UPPER: Water penetration after 60 min	g	≤ 0,2	-
UPPER: Water absorption after 60 min	%	≤ 30	-
INTERNAL LINING: Water vapour permeability	mg/(cm2*h)	≥ 2,0	130,7
INTERNAL LINING: Water vapour coefficient	mg/cm2	≥ 20	1045,8
OUTSOLE: Abrasion resistance	mm3	≤ 150	62
OUTSOLE: Energy absorption of seat region (E)	J	≥ 20	40
OUTSOLE: Flexural resistance	mm	≤ 4	0
OUTSOLE: Interlayer bond strength	N/mm	≥ 4	6,3
OUTSOLE: Resistance to fuel oil (FO)	%	≤ 12	3,9

Measurement Unit

ADDITIONAL FEATURES

Measurement Unit	Requirement	Results		
mA	≤ 1,00	-		
-	autsoles shall not melt and develop any cracks when bent	-		
°C	≤ 10	-		
°C	≤ 22	-		
cm2	after 80 min.	-		
MΩ	≤ 100	-		
	mA - °C °C cm2	mA ≤ 1,00 - autsoles shall not melt and develop any cracks when bent °C ≤ 10 °C ≤ 22 cm2 after 80 min.		

SOLE DESIGN AND PERFORMANCE



ENERGY ABSORPTION COEFFICIENT IN THE HEEL AREA

MINIMUM VALUE REQUIRED 20 TEST RESULT **75%**

INDUSTRIES

































STORAGE, CARE AND MAINTENANCE

- PANDA SAFETY footwear should be stored in original packaging, storage temperature should not exceed 35°C, humidity should be less than 80% and without the influence of direct sunlight.
- Sandals, shoes and boots should be cleaned after each use; dry off the shoes, not in proximity to or in direct contact with stoves or other sources of heat. • Carry out the periodic treatment of the uppers with suitable products containing wax, grease, silicone, etc.
- Avoid contact with aggressive chemicals and extreme temperatures.
- Verify the good state before each use.

